



**DSP 618D (Sn/Ag/Cu)  
LEAD FREE  
NO CLEAN DISPENSING  
SOLDER PASTE**

**CORPORATE HEADQUARTERS** USA: 315 Fairbank St. Addison, IL 60101<sup>1</sup> 630-628-8083<sup>1</sup> FAX 630-628-6543  
**EUROPE** UK: Unit 9 Apex Ct. Bassendale Rd. Bromborough, Wirral CH62 3RE<sup>1</sup> 44 151 334 0888<sup>1</sup> FAX 44 151 346 1408  
**ASIA-PACIFIC HEADQUARTERS** SINGAPORE: 6 Tuas South St. 5 Singapore 637790<sup>1</sup> 65 6795 7757<sup>1</sup> FAX 65 6795 7767  
**PHILIPPINES:** Phase 1 Qualitek Ave. Mariveles, Bataan Philippines C-2106 ! 6347 935 4119 ! FAX 6347 935 5608  
**CHINA:** 3B/F, YiPa Print Bldg. 351 # JiHua Rd., Buji Shenzhen, China 518112<sup>1</sup> 86 755 28522814<sup>1</sup> FAX 86 755 28522787

This data is based on information that the manufacturer believed to be reliable and offered in good faith. Qualitek International, Inc. makes no warranties expressed or implied as to its accuracy and assumes no responsibilities and liabilities arising out of its use by others as conditions and methods of use of the products is beyond the control of Qualitek International, Inc. The user must determine the suitability of the product before using it on a commercial basis. The warranties extend only to the conformity of the product to the physical descriptions. In no event will Qualitek International, Inc. be responsible for special, incidental and consequential damages whether the claim is in contract, negligence or otherwise. Qualitek specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.

**Description**

Qualitek has developed a no clean dispensing paste flux designed specifically for high temperature lead free alloys. DSP 618D is available in 10cc and 30cc syringes for easy dispensing for rework applications.

In addition, DSP 618D Lead Free solder paste exhibits superior joint strength and excellent wettability. The post soldering residues of DSP 618D are non-conductive, non-corrosive and highly insulated.

Main Features

- ❑ Low residues
- ❑ Long tack time
- ❑ Excellent wettability
- ❑ Hard non-conductive residues

**Technical Data**

	<b>Specification</b>	<b>Test Method</b>
<b>Flux Classification</b>	ROL0	JSTD-004
<b>Copper Mirror</b>	No removal of copper film	IPC-TM-650 2.3.32
<b>Silver Chromate</b>	Pass	IPC-TM-650 2.3.33
<b>Corrosion</b>	Pass	IPC-TM-650 2.6.15
<b>SIR</b>		
JSTD-004	4.23 x 10 <sup>11</sup> ohms	IPC-TM-650 2.6.3.3
<b>Electromigration</b>	Pass	Bellcore GR-78-CORE 13.1.4
<b>Post Reflow Flux Residue</b>	45%	TGA Analysis
<b>Acid Value</b>	110	IPC-TM-650 2.3.13
<b>Metal Loading</b>	87%	IPC-TM-650 2.2.20
<b>Viscosity</b>		
Malcom <sup>(2)</sup> , poise	85-110	IPC-TM-650 2.4.34.3 modified
Thixotropic Index	0.50-0.60	
<b>Slump Test</b>		
25 C, 0.63 vertical/horizontal	No bridges all spacings	IPC-TM-650 2.4.35
150 C, 0.63 vertical/horizontal	No bridges all spacings	IPC-TM-650 2.4.35
25 C, 0.33 vertical/horizontal	0.15 /0.15	IPC-TM-650 2.4.35
150 C, 0.33 vertical/horizontal	0.20/0.20	IPC-TM-650 2.4.35
<b>Solder Ball Test</b>	Pass	IPC-TM-650 2.4.43
<b>Tack</b>		
Initial	110 gm	JIS Z 3284
Tack retention @ 24 hr	89 gm	JIS Z 3284
Tack retention @ 72 hr	62 gm	JIS Z 3284

**Physical Properties**

**Solder Composition**

Qualitek Sn/Ag/Cu (Tin/Silver/Cu) alloys are designed as a lead-free alternative for Sn/Pb alloys for electronics assembly operations. Qualitek Sn/Ag/Cu alloys conform and exceed the impurity requirements of J-STD-006 and all other relevant international standards.

<b>Typical Analysis</b>														
	Sn	Ag	Cu	Pb	Sb	Bi	In	As	Fe	Ni	Cd	Al	Zn	Au
<b>LF955-38</b>	Bal	3.6-4.0	0.5-0.9	0.070 Max	0.200 Max	0.100 Max	0.100 Max	0.030 Max	0.020 Max	0.010 Max	0.002 Max	0.005 Max	0.003 Max	0.050 Max
<b>LF958-35</b>	Bal	3.3-3.7	0.5-0.9	0.070 Max	0.200 Max	0.100 Max	0.100 Max	0.030 Max	0.020 Max	0.010 Max	0.002 Max	0.005 Max	0.003 Max	0.050 Max
<b>LF965-30</b>	Bal	2.8-3.2	0.3-0.7	0.070 Max	0.200 Max	0.100 Max	0.100 Max	0.030 Max	0.020 Max	0.010 Max	0.002 Max	0.005 Max	0.003 Max	0.050 Max
<b>LF217</b>	Bal	3.8-4.2	0.3-0.7	0.070 Max	0.200 Max	0.100 Max	0.100 Max	0.030 Max	0.020 Max	0.010 Max	0.002 Max	0.005 Max	0.003 Max	0.050 Max

	Sn/Ag/Cu	Sn63/Pb37
Melting Point, °C	217-221	183 E
Hardness, Brinell	15HB	14HB
Coefficient of Thermal Expansion	Pure Sn= 23.5	24.7
Tensile Strength, psi	4312	4442
Density, g/cc	7.39	8.42
Electrical Resistivity (μohm-cm)	13.0	14.5
Electrical Conductivity, %IACS	16.6	11.9

	Sn/Ag/Cu	Sn63/Pb37
Yield Strength, psi	3724	3950
Total Elongation,%	27	48
Joint Shear Strength, at 0.1mm/min 20 °C	27	23
Joint Shear Strength, at 0.1mm/min 100 °C	17	14
Creep Strength, N/mm <sup>2</sup> at 0.1mm/min 20 °C	13.0	3.3
Creep Strength, N/mm <sup>2</sup> at 0.1mm/min 100 °C	5	1
Thermal Conductivity, W/m.K	58.7	50.9

**Particle Size**

SAC alloys are available in 3(45-25μm), 4(38-20μm) and 5(25-15μm) J-STD-005 powder distribution. Solder powder distribution is measured utilizing laser diffraction, optical analysis and sieve analysis. Careful control of solder powder manufacturing processes ensures the particles' shape are 95% spherical minimum (aspect ratio < 1.5) and that the alloy contains a typical maximum oxide level of 80 ppm.

**Metal Loading**

Typical metal loading for stencil printing application is **86-87%**. Compared to typical Sn63/Sn62 dispensing solder pastes manufactured with 88% by weight metal loading, DSP 618D Lead Free provides as much as 10-12% higher metal volume than Sn63/Sn62. This increased in volume of DSP 618D promotes better wetting and spreading of Sn/Ag/Cu alloys.

**Dispensing**

Needle Gauge	Needle inner diameter		Applicable powder
	in.	µm	(mesh cut)
18	0.033	838	-200+325
20	0.023	584	-325+500
21	0.020	508	-325+500
22	0.016	406	-325+500
23	0.013	330	-325+500
25	0.010	254	-400+635
27	0.008	203	-500

The clearance gap between the needle and the substrate affects the shape and quality of the dot dispensed. If the clearance is too little, the dot tends to be flattened out, and if too large, the dot tends to have long tailing.

**Pressure**

The pressure applied in the syringe should be kept at a minimum, and the proper head pressure kept in the range of 15-25 lb/in<sup>2</sup> (1.05-1.76 kg/cm<sup>2</sup>). In cases where a paste requires much higher pressure (more than 40 lb/in<sup>2</sup> or 2.82 kg/cm<sup>2</sup>) to dispense, the paste will become inconsistent and clogging may be expected. The external air pressure supply should be maintained constant.

**Open & Abandon Time**

Tests have proven that DSP618D will perform during continuous dispensing for up to 8 hrs. The paste can be left in the dispensing unit for up to 4 hours without paste drying out. If extended downtime is expected (>4 hrs), the whole dispensing sysem should be flushed without leaving any paste in any part of the system.


**Paste Application**

Solder paste should be taken out of the refrigerator at least 3 to 6 hours prior to use. This will give the paste enough time to come to thermal equilibrium with the environment. The flow rate of paste in a dispensing application depends on viscosity, which cn be altered by temperature change. If solder paste is supplied in syringes pre-mixing is not necessary due to the shear action produced from the dispensing.

**Reflow**

Best results have been achieved when DSP 618D is reflowed in a **forced air convection** oven with a minimum of 8 zones (top&bottom), however reflow is possible with a 4 zone oven (top & bottom).

The following is a recommended profile for a forced air convection reflow process. The melting temperature of the solder, the heat resistance of the components, and the characteristics of the PCB (i.e. density, thickness, etc.) determine the actual reflow profile.



**Preheat Zone-** The preheat zone, is also referred to as the ramp zone, and is used to elevate the temperature of the PCB to the desired soak temperature. In the preheat zone the temperature of the PCB is constantly rising, at a rate that should not exceed 2.5 C/sec. The oven’s preheat zone should normally occupy 25-33% of the total heated tunnel length.

**The Soak Zone-** normally occupies 33-50% of the total heated tunnel length exposes the PCB to a relatively steady temperature that will allow the components of different mass to be uniform in temperature. The soak zone also allows the flux to concentrate and the volatiles to escape from the paste.

**The Reflow Zone-** or spike zone is to elevate the temperature of the PCB assembly from the activation temperature to the recommended peak temperature. The activation temperature is always somewhat below the melting point of the alloy, while the peak temperature is always above the melting point.

**Cleaning of Flux Residues**

DSP 618D is a no clean formulation therefore the residues do not need to be removed for typical applications. If residue removal is desired, the use of Everkleen 1005 Buffered Saponifier with a 5-15% concentration in hot 60 °C (140 °F) will aid in residue removal.

## **Storage & Shelf Life**

It is recommended that solder paste be stored at a temperature of between 35-50°F (2-10°C) to minimize solvent evaporation, flux separation, and chemical activity. If room temperature storage is necessary it should be maintain between 68-77°F (20-25°C).

### ***Shelf life***

Unopened Container (35-50°F/2-10°C) 6 months (from DOM)

Unopened Container (68-77°F/20-25°C) 3 months (from DOM)

## **Working Environment**

Solder paste performs best when used in a controlled environment. Maintaining ambient temperature of between 68-77°F (20-25°C) at a relative humidity of 40-65% will ensure consistent performance and maximum life of paste.

## **Disposal**

DSP 618D should be stored in a sealed container and disposed of in accordance with state & local authority requirements.

## **Packaging**

10cc syringe	35 gm
30cc syringe	100 gm
4 oz. jar	250 gm